



613

SOLVENT BASED ADHESIVE

KEY FEATURES

- High grab
- High shear strength
- Good temperature resistance

DESCRIPTION

Bostik 613 is a Toluene free solvented contact adhesive exhibiting high initial grab. It can be easily applied by brush or spreader; the resultant bonds give excellent bond strength, high shear strength and good temperature resistance.

RECOMMENDED USE

Bostik 613 is a general purpose, contact adhesive particularly suitable for bonding plastic laminates and other rigid plastics (excluding polyethylene & polypropylene) on particleboard, MDF, woods, metals and all types of board with the exception of bituminous materials.

Bostik 613 may also be used to bond boards of insulating and cane fibre, rigid polyurethane foam, laminated panels and acoustic tiles to suspended or vertical surfaces such as flat surfaced ceilings or walls. Most types of rigid plastic nosings and covings may also be bonded. **Bostik 613** is intended for interior use. It is not suitable for use with expanded polystyrene foam and is also unsuitable for use where only point contact is obtainable between the surfaces to be bonded.

IMPORTANT

Before embarking on any work involving **Bostik 613** the safety data sheet should be carefully studied by those carrying out the work.

METHOD OF USE

SURFACE PREPARATION

- Substrates to be bonded should be perfectly clean dry and free from dust and grease.
- Smooth or polished surfaces should first be roughened with fine abrasive.
- If degreasing is necessary, a detergent/water treatment should first be considered. If this is inappropriate a suitable solvent e.g. **Bostik Cleaner 5** may be used. It is advisable to check the effects of degreasing solvents on plastics, rubber materials and painted surfaces before carrying out the operation. All traces of cleaning solvents must be allowed to evaporate completely before application of the adhesive.

APPLICATION

- **Bostik 613** can be applied by brush or serrated spreader.
- Apply an even ribbed coat of adhesive to both surfaces using a serrated trowel or spreader. For correct coverage use the spreader at such an angle as to give good rib formation after drying. If a white "bloom" appears on the surface, raise the temperature and/or dry the atmosphere.

ADDITION OF ACCELERATOR FOR INCREASED HEAT RESISTANCE

- For temperature resistance above 60°C stir into the adhesive an addition of 5% **Accelerator F** (by weight) then use in the normal way.
- The mixture has a pot life of approx. 4 hours.

DRYING

- Drying time depends on film thickness, surface porosity, temperature and humidity.
- **Minimum drying time 20 minutes** - this is to ensure thorough drying of the adhesive film, the surface may feel touch dry prior to this but bonding too early can cause problems of solvent entrapment, resulting in poor bonding.

NORMAL BONDING METHOD

- Bring the two dry, coated surfaces into contact within 60 minutes of application and press together over the entire bond area.
- To obtain optimum initial bond strength, surfaces should be bonded as soon as possible after recommended drying time.
- Apply as much pressure as possible by hand roller, static press or nip roller without causing damage. Sustained pressure is not necessary.
- Bringing the surfaces together before the surfaces are touch dry will result in solvent being trapped, adversely affecting the final bond, and possibly giving rise to blistering problems.
- The initial bond strength allows immediate handling, but maximum bond strength is reached after 24 - 48 hours.

SPECIAL BONDING METHODS

In some applications it is convenient to pre-coat components some time before assembly is required. **Bostik 613** may be adapted to this type of use by means of reactivation processes. The adhesive film must be kept free from contamination.

Reactivation by heat

The dried adhesive film may be reactivated by heating to a temperature of 85 - 95°C. A battery of 4 x 250W infrared lamps placed 200-250mm above the coated surface will provide adequate reactivation in 30 - 90 seconds. The actual time being dependent on the nature and/or colour of the substrate.

Reactivation by solvent

Pre-coated areas may also be reactivated by a brush coat of **Bostik Cleaner 3**, normally to only one of the surfaces. The bond should not be made until the activated film has reached a touch dry condition.

GENERAL PRECAUTIONS

- Do not add anything to the adhesive to modify its properties.
- After each use, close the container tightly in order to avoid solvent evaporation.

TYPICAL CHARACTERISTICS	
Physical Form	Moderately viscous liquid
Colour	Amber
Chemical Type	Polychloroprene rubber/ synthetic resin blend
Solvent	Ester/Ketone/ hydrocarbon blend
Flammability	Highly Flammable
Viscosity Brookfield RVT 10rpm at 25°C [mPa.s]	Approx. 3750
Total Solids Content [%]	Approx. 23
Relative Density	Approx. 0.84
Cleaner	Bostik Cleaner 3

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, or its liability for fraud, or fraudulent misrepresentation, or any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including

BSI STANDARDS



PACKAGING

For current pack sizes please contact the Customer Service Department.

STORAGE

Store in accordance with the requirements of the petroleum regulations in a dry flameproof area between 5 and 25°C.

SHELF LIFE

At least 18 months closed in original container stored under the above conditions

in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number on the bottom right hand side of this page.

SMART HELP

Please contact your local representative

